

	Transmittance	Polarizing Efficiency	Surface Treatment	Thickness
AMN-3244EVK	41.8 %	99.8 %	Clear	215 μm
AMN-3244EVAG25K			Anti Glare(Haze : 25%)	
AMN-5244EVK			Clear	175 μm
AMN-5244EVAGSRK			AG Super resolution (Haze : 42%)	
AMN-0244TP	42.8%	99.9 %	Clear	127 μm
AMN-02444AG25			Anti Glare(Haze : 25%)	
AMN-0244AGSR			AG Super resolution (Haze : 42%)	
AMN-0244HC			Hard Coating	
AMN-0244LR	43.7%	99.9 %	Low reflection (Ratio : $\leq 1.5\%$)	132 μm
AMN-0244TB	42.0%	99.9%	DBEF	163 μm
AMN-2242TB				123 μm